




### Process Flow



### Typical Physical Parameters of Silica sand

Test Parameters	Unit	
Holcim Blu	Mg/Gm	0.01
Flow Coefficient (Graded)	Seconds	13.02
Flow Coefficient (As it is)	Seconds	13.81

Test Name	Result
Water Absorption	0.77
Dry Loose Bulk Density (Kg/Lit)	1.51
Dry Rodded Bulk Density (Kg/Lit)	1.66
Specific Gravity	2.67
Material Finer than 75 micron	0.33